



Automotive Aftermarket Division

3M™ 08868/08878/08879 Antichip Coatings

1) Part Numbers

3M™ 08868	:	Black / 1 litre
3M™ 08878	:	White / 1 litre can
3M™ 08879	:	Grey / 1 litre can

2) Description and end uses

The 3M™ 08868/78/79 rubberised coatings provide stone chip protection. They have excellent sound deadening and rust preventive properties. They are fast drying and over paintable.

Key features:

- Easily applied using 3M™ 08996 spray gun or 3M™ 16587 HGP system including PPS cup, liner and nozzle
- Fast drying / tack free time
- Weathering, stone chip and corrosion resistant
- Flexible
- Excellent coverage in one coat. No flow

3M™ 08868/78/79 can be used to restore textured finishes on new parts or repaired panels in the following areas:

- Wheel arches
- Front/rear valences
- Side sills
- Wings

***NOTE:** 3M™ 08868 black coating can be used as an undercoating and body coating because it is over paintable.*



Technical Data Sheet

Effective: 28/02/2020 Supersedes: 21/01/1999

3) Physical Properties

Base	Rubber
Solvent	Mixed hydrocarbons
% Solids	Approx. 50 %
Density	About 1.1
Viscosity (Brookfield) (Spindle 3, speed 10 rpm)	6000 cps
Thixotropic index	5
Tack free time	15 minutes
Coverage	2-3 sqm / kg
Storage conditions	Cool dry place. Best results are obtained when material is stored and applied at room temperature, 15 to 30°C. Storage temperature must not exceed 50°C.
Shelf life	2 years from date of manufacture under normal storage conditions. Refer "Lot Number" and "Best Before Date" on can.

4) Directions for Use

1-Preparation

Surfaces should be free from dirt and oil
Make sure the 3M™ 08996 applicator is clean, security holes free
Screw the can to the gun and fix air line

Caution: Shake the can well before opening

2-Typical Application with 08996

Use a pressure from 4 to 6 bars (55-80 PSI)
Spray at a distance from 25 to 50 cm depending on the desired texture.

Note: Different types of texture can be achieved by adjusting the nozzle (the more closed the nozzle, the finer the texture), the air pressure/spray distance combination or the number of coats.

For many coats, allow the coating to dry for a couple of minutes



Technical Data Sheet

Effective: 28/02/2020 Supersedes: 21/01/1999

Depending on the curing conditions (temperature, humidity...) the coating should be overpainted with a primer when painting with water-based materials and after 1 to 3 hours drying.

3-Typical Application with HGP System

Use a pressure from 1.5 to 2 to bar (20-30 PSI)

Spray at a distance from 25 to 50 cm depending on the desired texture.

Note: Different types of texture can be achieved by adjusting the spray gun fluid control, set the fan control at ¼ from close. The air pressure/spray distance combination or the number of coats.

For many coats, allow the coating to dry for a couple of minutes

Depending on the curing conditions (temperature, humidity...) the coating should be overpainted with a primer when painting with water-based materials and after 1 to 3 hours drying.

5) Storage

Store at room temperature in flammables storage area. Rotate stock on a “first-in-first-out” basis. When stored at the recommended conditions in original, unopened containers, this product has a shelf life see container for details. Use in a well-ventilated area.

6) Safety

3M™ Antichip Coatings are designed FOR PROFESSIONAL USE ONLY.

7) Disclaimer

All statements, technical information and recommendations are based on tests we believe to be reliable but the accuracy or completeness thereof is not guaranteed. Please ensure before using our product that it is suitable for your intended use. All questions of reliability relating to this product are governed by the Terms of Sale subject, where applicable, to the prevailing law.



Technical Data Sheet

Effective: 28/02/2020 Supersedes: 21/01/1999

For Additional Health and Safety Information

3M South Africa & Sub-Saharan Africa, 146A Kelvin Drive, Woodmead, Sandton, South Africa, Tel: (0861) 225536
3M (East) AG Representation Office Tirane, Rruga Sami Frasheri, Pallati i Ri Perxhola Kati 2 Ap2, 1000 Albania
3M Arabia, LLC, Building 24-25 3M Saudi Arabia Zone C, Business Gate, Airport Road, Riyadh, Saudi Arabia
3M Bulgaria, Mladost 4, Business Park, bl.4, 2nd floor, Sofia 1766, Bulgaria
3M Česko, spol. s r.o., V Parku 2343/24, 148 00 - Praha 4, Czech Republic
3M (East) AG, Branch office Croatia, Avenija Većeslava Holjevca 40, 10 000 Zagreb, Croatia, Tel: +385 1 2499750, www.3m.com.hr
3M Egypt, Finance Center , New Cairo , Plot 140 , Banking Sector , 5th settlement , Cairo , Egypt
3M Hellas MEPE, Automotive Aftermarket Division, 20 Kifisias Avenue, 151 25 Marousi, Greece, Phone: +30 210 68 85 300, innovation.gr@mmm.com, www.3M.gr
3M Hungária Kft, Neumann János u. 1/E, 1117 Budapest, Hungary
3M Israel, 91 Medinat Hayehudim St., Herzliya, Israel
3M Kenya Ltd, Victoria Towers, 3rd Floor, Kilimanjaro Av, Upperhill, Kenya
3M Gulf Limited, Ein El Mreisseh, Saint Charles City Center, 4th. Floor, P.O.Box: 11-5025, Riad el Solh, Beirut 1107 2180 Lebanon
3M Minnesota Mining & Manufacturing Nigeria Limited, No 2 Sheraton Opebi Link Road, Ikeja, Lagos Nigeria
3M Pakistan, Islamic Chamber of Commerce Building, ST-2/A, Block 9, KDA Scheme 5, Clifton, Karachi, Pakistan
3M Poland, Al. Katowicka 117, Kajetany, 05-830 Nadarzyn, Poland, Telefon: +48 22 739 60 00, www.3m.pl/kontakt
3M Gulf (Representation Office), Suhaim Bin Hamad St., Al Mana Towers Tower B, 2nd Floor, Office No.4, Doha Qatar, P.O.Box 14685
3M Romania, 12 Menuetului St., Bucharest Business Park, Building D, District 1 013713 Bucharest, Romania
3M (East) AG, Representation Office Serbia, Airport City, Omladinskih brigada 90B, 11070 Belgrade, Serbia, Tel: +381 11 2209 400, www.3m.co.rs/3M/sr_RS/3m-south-east-europe/
3M Slovensko s.r.o., Polus Tower 2, Vajnorská 100/B, 83104 Bratislava
3M (East) AG, Branch office Slovenia, Cesta v Gorice 8, 1000, Ljubljana, Slovenia, Tel: +386 1 2003 630, www.3m.com/3M/sl_SI/3m-south-east-europe/
3M Sanayi ve Ticaret As, Barbaros Mah., Mor Sümbül Sok., No:7/3F, 27-51, Nidakule Ataşehir Güney, 34746 Ataşehir, İstanbul, Turkey
3M Gulf Limited, Dubai Internet City, Building No. 11, 3rd Floor, U.A.E

© 3M 2019. 3M is a trademark of the 3M company. All rights reserved